



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61F 2/02	A1	(11) International Publication Number: WO 93/14718 (43) International Publication Date: 5 August 1993 (05.08.93)
(21) International Application Number: PCT/US93/00982 (22) International Filing Date: 28 January 1993 (28.01.93) (30) Priority data: 828,011 30 January 1992 (30.01.92) US (71) Applicant: ETEX CORPORATION [US/US]; University Park at MIT, 38 Sidney Street, The Clark Building, Cambridge, MA 02139 (US). (72) Inventor: LEE, Dosuk, Duke ; 50 Longwood Avenue, Brookline, MA 02146 (US). (74) Agent: CLARK, Paul, T.; Fish & Richardson, 225 Franklin Street, Boston, MA 02110-2804 (US).		(81) Designated States: CA, JP, RU, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: ELECTROPHORETIC DEPOSITION OF CALCIUM PHOSPHATE MATERIAL ON IMPLANTS (57) Abstract The invention features a method for preparing coated implants. The method includes the steps of: (a) providing a gel of amorphous calcium phosphate having a calcium to phosphorous ratio of 0.5 to 1.6; (b) dispersing the gel of amorphous calcium phosphate in an aqueous liquid to form a colloidal mixture which is between 60 % and 99 % by weight water; (c) immersing an implant to be coated in the colloidal mixture; and (d) with the implant acting as an anode, electrodepositing material in the colloidal mixture on the implant to form a substantially uniform coating.		

FOR THE PURPOSES OF INFORMATION ONLY .

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

- 1 -

**ELECTROPHORETIC DEPOSITION OF CALCIUM
PHOSPHATE MATERIAL ON IMPLANTS**

Background of the Invention

5 The field of the invention is coatings for orthopedic implant materials.

 Orthopedic implants are commonly coated with bioactive ceramics, particularly calcium phosphate (a naturally-occurring bone mineral), to provide a surface
10 suitable for the ingrowth of bone tissue. The ingrowth of bone tissue results in secure fixation of the implant to existing bone. It is known in the art that coatings may be applied to an implant by slip casting, plasma spraying, and electrophoretic deposition.

15 Ducheyne et al. (U.S. Patent 4,990,163) disclose the use of powdered calcium phosphate compounds dissolved in isopropanol for electrophoretic deposition of a bioactive coating on implant surfaces. The coating is said to have a high dissolution rate.

20 Phillips et al. (U.S. Patent 3,892,648) disclose the electrophoretic deposition of bone particles in a collagen-bearing medium on orthopedic implants. Collagen fibrils are dispersed in a gelatin medium; the resulting gelled collagen is next dispersed in a water/glycerine
25 solution, and finely divided bone is added to the solution. The solution is used in an electrophoretic deposition process to create a coating of bone and collagen on an implant surface.

Summary of the Invention

30 In general, the method features a method for preparing coated implants. The method includes the steps of: (a) providing a gel of amorphous calcium phosphate having a calcium to phosphorous ratio of 0.5 to 1.6; (b) dispersing the gel of amorphous calcium phosphate in

- 2 -

an aqueous liquid to form a colloidal mixture which is between 60% and 99% by weight water; (c) immersing an implant to be coated in the colloidal mixture; and (d) with the implant acting as an anode, electrodepositing material in the colloidal mixture on the implant to form a substantially uniform coating. The method is especially well-suited to coating of metals for use as orthopedic implants. The gel has a calcium to phosphorous ratio of between 0.5 and 1.6 at a pH of between 8 and 14, preferably 11.

In preferred embodiments, the gel is comprised of a mixture of calcium nitrate, di-ammonium hydrogen phosphate, and ammonium hydroxide; and the aqueous liquid is essentially water.

In another preferred embodiment, the method includes the step of sintering the coated implant subsequent to step (d).

In a more preferred embodiment, the sintering is performed at between 600°C and 1350°C. In a still more preferred embodiment, the sintering is performed in air.

The method of the invention creates a uniform finely-crystalline on the implant surface. The coated implant can be sintered. The resulting coating is fine-grained, well-crystallized hydroxyapatite. The surface has superior mechanical strength and is substantially insoluble in aqueous environments.

Other features and advantages of the invention will be apparent from the following description of the preferred embodiments thereof, and from the claims.

Detailed Description

Described below are techniques for preparing a gel of amorphous calcium phosphate, preparing a colloidal mixture of the gel and an aqueous solution, electrophoretically depositing material in the solution

- 3 -

on an implant surface, and sintering the coated material to produce a coating of hydroxyapatite.

A gel of amorphous calcium phosphate is prepared from an aqueous solution of calcium nitrate $[\text{Ca}(\text{NO}_3)_2]$,
5 di-ammonium hydrogen phosphate $[(\text{NH}_4)_2\text{HPO}_4]$, and ammonium hydroxide $[(\text{NH}_4)(\text{OH})]$ as described by LeGeros (Calcium Phosphate in Oral Biology and Medicine, *Monographs in Oral Science*, vol. 15, Meyers, ed., Basel: Karger, 1991, p. 201). Briefly, a 0.2M to 0.5M (preferably 0.32M)
10 solution of calcium nitrate is made basic by the addition of 5% to 10% (preferably 7.3%) ammonium hydroxide by volume; a 0.1M to 0.3M (preferably 0.15M) solution of di-ammonium hydrogen phosphate is made basic by the addition of 1% to 5% (preferably 3.1%) ammonium hydroxide by
15 volume. One part of the calcium nitrate solution is quickly added to 2 to 3 parts (preferably 2.4 parts) of the di-ammonium hydrogen phosphate solution with vigorous stirring to create a solution having a calcium to phosphorous ratio of 0.5 to 1.6, preferably approximately
20 0.9. The pH of the resulting solution is between 8 and 14 (preferably 11). The solution rapidly develops into a colloidal gel which is filtered and washed in water to remove excess ammonium ions. Infrared spectroscopy may be used to check for the presence of excess ammonium
25 ions. Washing for approximately 24 hours is adequate. An electrophoretic solution is prepared by mixing 1 to 40% by weight gel with water. The solution is stirred vigorously to disperse the gel into a fine colloidal solution. The solution is used in the electrodeposition
30 described below.

The material to be coated is thoroughly cleaned prior to electrodeposition. In the case of titanium alloys, this can be accomplished by polishing with emery cloth, followed by ultrasonic cleaning in alcohol and
35 etching in a dilute solution of nitric and hydrofluoric

- 4 -

acid. During electrodeposition the material to be coated serves as the anode and is suspended in the above-described colloidal solution. The deposition itself is conducted under conditions of constant current at 1 to 5 100 mA, preferably approximately 5 mA. Alternatively, the deposition may be conducted under conditions of constant voltage at 1 to 35 volts, preferably approximately 32 volts. During deposition the temperature of the solution may be between room 10 temperature and 100° C, preferably approximately 40° C.

The distance between the anode and cathode during deposition is preferably between 1 and 20 cm. A preferred geometry places the anode to be coated at the center of a radially symmetric array of cathodes or a 15 cylindrical cathode.

The above-described procedure produces a uniform, finely crystalline coating of calcium phosphate on the substrate which is next sintered at 600° C to 1350° C in air (preferably 900°C) for 1 to 12 hrs, preferably 20 approximately 2.5 hrs.

Analysis of the coating by x-ray diffraction and infrared spectroscopy indicates that the coating created is composed of fine-grained, well-crystallized hydroxyapatite. Tests of shear and tensile strength 25 indicates that the coating produced in this fashion has excellent mechanical properties.

What is claimed is:

- 5 -

1. A method for preparing a coated implant, said method comprising the steps of:

(a) providing a gel of amorphous calcium phosphate having a molar ratio of calcium to phosphorous of 0.5 to
5 1.6;

(b) dispersing said gel of amorphous calcium phosphate in an aqueous liquid to form a colloidal mixture which is between 60% and 99% by weight water;

(c) immersing an implant to be coated in said
10 colloidal mixture; and

(d) with said implant acting as an anode, electrodepositing material in said colloidal on said implant to form a substantially uniform coating.

2. The method of claim 1 wherein said gel is
15 comprised of a mixture of calcium nitrate, di-ammonium hydrogen phosphate, and ammonium hydroxide having a calcium to phosphorous ratio of between 0.5 and 1.6.

3. The method of claim 1, further comprising sintering said coated implant subsequent to step (d).

20 4. The method of claim 3 wherein said sintering step is performed at between 600 and 1350°C.

5. The method of claim 4 wherein said sintering step is performed in air.

6. The method of claim 1 wherein said aqueous
25 liquid is essentially water.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US93/00982

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :A61F 2/02

US CL :623/11

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 623/16,18,66;427/2

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
Please See Extra Sheet.

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A, 4,868,287 (Sikes et al.) 19 September 1989, See column 9 lines 17-25.	1
A	US,A, 4,944,754 (Linkow et al.), 31 July 1990, see column 2 lines 5-34.	1
A,P	US,A, 5,125,971 (Nonami et al.), 30 June 1992, see column 4 lines 41-55.	1

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:	* T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
* A* document defining the general state of the art which is not considered to be part of particular relevance	* X	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
* E* earlier document published on or after the international filing date	* Y	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
* L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	* A*	document member of the same patent family
* O* document referring to an oral disclosure, use, exhibition or other means		
* P* document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

16 APRIL 1993

Date of mailing of the international search report

10 JUN 1993

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Authorized officer

DINH NGUYEN

Facsimile No. NOT APPLICABLE

Telephone No. (703) 308-0858

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US93/00982

B. FIELDS SEARCHED

Electronic data bases consulted (Name of data base and where practicable terms used):

Automated Patent System;

Amorphous

Calcium phosphate

coating

electrophoretic